



# TECHNICAL DATA SHEET

**JOHN C. DOLPH COMPANY**

P.O. Box 267  
320 New Road  
Monmouth Junction, NJ  
08852

Ph:(732) 329-2333  
Fax:(732) 329-1143  
info@dolphs.com  
www.dolphs.com

## **SYNTHITE® AC-43**

### **CLEAR AIR DRYING VARNISH**

#### **PRODUCT DESCRIPTION**

AC-43 is a high temperature; fast cure, air dry, modified polyester varnish. Perfect for dip or spray applications where a clean clear protective coating is needed over various electric apparatus.

#### **FEATURES & BENEFITS**

- Quick drying
- Toughness and flexibility
- Good penetration
- Heat resistant
- Fast cure cycles
- Solderable
- Acid and alkali resistant
- UL Systems to 180°C

#### **TYPICAL APPLICATIONS**

- Stator Windings
- Coils
- Transformers
- Printed Circuit Boards
- Resistors
- Capacitors

#### **TYPICAL PROPERTIES**

##### **Physical**

<b>Appearance/Color</b>	<b>Clear/Amber</b>
<b>Density @ 77°F (25°C), Lbs/gal</b>	<b>7.0 –8.0</b>
<b>Viscosity @ 77°F (25° C), Brookfield Viscometer, cps</b>	<b>20 – 70</b>
<b>Viscosity Dolph's viscosimeter @ 77°F</b>	<b>15 – 18 sec.</b>
<b>Film Build, mils/side, ASTM D-115</b>	<b>1 - 1.5</b>
<b>Flash Point, °F</b>	<b>54</b>
<b>Thinner (solvent)</b>	<b>T-200X Thinner (solvent)</b>
<b>Air Drying Time on Copper Strip, ASTM D-115, Min.</b>	<b>Set to Touch Tack Free</b>

All statements, technical information and recommendations related to Sellers' products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before using the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liabilities whatsoever in connection with such use. The statements contained herein are made in lieu of all warranties, expressed or implied. Seller shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or inability to use its products. The sole liability of John C. Dolph Co., Inc. for any claims arising out of the manufacture, use or sale of its products shall be for the buyer's purchase price.

Appearance/Color	Clear/Amber
VOC Content, ASTM D 6053, lbs/gal	4.3
Corrosive Effect on Copper	None

### Electrical

Dielectric Strength, ASTM D115, volts/mil	Dry	2,000
	Wet	1,200

### Chemical Resistance

Water	Excellent
Acid (10% Sulfuric Acid)	Excellent
Alkali (1% Sodium Hydroxide)	Excellent
Salt Water	Excellent
Oil, ASTM D-115	Passed

### Thermal Class (UL-1446)

Twisted Pair	MW-24	155
	MW-28	130
	MW-35	180

## APPLICATION GUIDELINES

AC-43 may be applied by brushing, dipping, or spray. It will air dry in one hour but can be baked to improve its chemical and oil resistance. A 10-15 minutes bake at 300°F will provide a film with optimum toughness and bond strength.

For fast conveyor operation, the following cycle is recommended. We recommend that all ovens be preheated prior to the units being preheated and/or cured.

**NOTE:** AC-43 should be thinned 15% by volume for this type of cycle.

1. Preheat 10 minutes at 300°F.
2. Dip 15 seconds, or until bubbles have stopped.
3. Drain 45 seconds.
4. Bake 5 minutes at 330°F.

## STORAGE AND SHELF LIFE

Shelf life is one year from date of shipment from our plant, when stored in closed containers at 70°F or below.

1. Store in cool, dry place at 70°F/21°C or below.
2. Protect from direct sunlight and sources of heat

3. Keep away from heat, sparks and open flame.

**SAFETY AND ENVIRONMENT**

Avoid contact with skin and eyes. See Material Safety Data Sheet

AUTHORIZED DISTRIBUTOR