51587

POLYESTER FILM ELECTRICAL TAPE

INTERTAPE POLYMER GROUP®

TECHNICAL DATA SHEET

DESCRIPTION

This combination of a tough, conformable polyester backing and rubber thermosetting adhesive may be used for a variety of electrical applications. This tape is abrasion and puncture resistant, resists chemicals and solvents when thermoset, and has excellent electrical insulating properties.

PRODUCT APPLICATIONS

Coil wrapping, anchoring, harnessing, holding, insulating tabbing and inter-layer insulating.

GOVERNMENT COMPLIANCE

MIL-I-15126F, Type MF-2.5

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing Polyester

Backing Thickness 1.0 mil (0.025 mm)

Adhesive Rubber Thermosetting

Color Yellow, Black

Total Thickness 2.2 mil (0.056 mm)

Dielectric Strength 5000 Volts **Temp/Class** 130°C / B

Insulation Resistance 10⁶ megohms

Tensile Strength 25 lbs/in (44 N/cm) **Adhesion to Steel** 50 oz/in (5.5 N/cm)

Elongation 100%

Electrolytic Corrosion 1.0 Direct/ A, 1*

Flammability BU 1*

Storage StabilityVery GoodSolvent ResistanceVery GoodMoisture ResistanceExcellentUL File #E20780CSA File #LR94980

*VDE 0340



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 11/13



