

2255

FILM-PTFE (SKIVED, HIGH-MODULUS)

Saint-Gobain Performance Plastics CHR® 2255 is manufactured from modified high-modulus PTFE (polytetrafluoroethylene) film coated with high-temperature silicone adhesive.

Typical Properties

Product Number	2255-2	2255-3	2255-5	2255-6
Backing Material	Film-PTFE	Film-PTFE	Film-PTFE	Film-PTFE
Adhesive Type	Silicone	Silicone	Silicone	Silicone
Total Thickness (in.)	.0035	.0045	.0065	.0075
Backing Thickness (in.)	.0020	.0030	.0050	.0060
Adhesive Thickness (in.)	.0015	.0015	.0015	.0015
Adhesion to Steel (oz./in.)	30	35	40	45
Tensile Strength (lbs./in.)	30	45	60	65
Dielectric Strength (volts)	9000	11000	15000	18000
Elongation (% at break)	150	175	275	200
Operating Temperature (°F)	-100 to 500	-100 to 500	-100 to 500	-100 to 500
Color	Gray	Gray	Gray	Gray

Values shown are typical. Certified test reports for writing specifications are available.

Applications—The excellent dielectric properties of this product combined with its high-temperature adhesive coating make **2255** an excellent choice as a high-temperature insulation product. **2255** is used in phase insulation for bundling end turns, spot bundling and anchoring breakouts. The aerospace industry also uses **2255** to protect airframe wire harnesses.

Features/Benefits—**2255's** most outstanding properties are its high dielectric and tensile strength, which make it an extremely durable insulation tape. The high temperature properties of the PTFE and silicone adhesive allow **2255** to perform in continuous temperatures up to 500°F. A high-modulus tape, **2255** also exhibits low elongation which enables it to be applied with

automatic wrapping equipment. The other outstanding features of **2255** include chemical inertness as well as low-friction, anti-stick and non-toxic properties, making it the right material for numerous applications. **2255** meets MIL-I-23594C government specifications.

Availability—**2255** is available in 2, 3, 5 and 6 mil thickness. Factory stock for **2255** is in master log form 36 yards long x 16" wide. Rolls can be slit in widths ranging from 1/4" to 16". **2255** can also be etched on the topside for bondability and may as well be supplied with a release liner. **2255-2** is also available with a pigmented black adhesive — properties are unchanged.

Saint-Gobain Performance Plastics Corporation
14 McCaffrey Street
Hoosick Falls, NY 12090
Customer Service: (800) 962-2666
Tel: (518) 686-7301
Fax: (800) 526-8479, (518) 686-4840

www.fff.saint-gobain.com

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

CHR® is a registered trademark
©2004 Saint-Gobain Performance Plastics Corporation
AFF-1130-PDF-0304-SGCS